

**WEITACK® C5 HYDROCARBON RESIN**

**MA6110**

**Properties:**

MA6110 is aliphatic hydrocarbon resin with narrow molecular weight distribution.

**Detailed Specification:**

Color (Gardner 1:1)	3 Max.	ASTM D 1544
Softening Point (Ring & Ball, 'C)	90-96	ASTM E 28
Melt Viscosity (160'C, cps)	500-800	ASTM D 3236

**Typical Datas:**

Softening Point (Ring & Ball, 'C)	93	ASTM E 28
Color (Gardner 1:1)	2.8	ASTM D 1544
Color Stability (200'C, Gardner 1:1)	5	ASTM D 1544
Acid Value (KOHmg/g)	0.02	ASTM D 974
Melt Viscosity (160'C, cps)	700	ASTM D 3236
Mn	1200	GPC
Mw	1800	GPC

**Application:**

MA6110 used as tackifier for PSA and HMA, with good compatibility with base polymers like EVA, SIS, metallocene polyolefins, natural rubber, synthetic polyisoprene and Butyl rubber

**Package:**

25kg Kraft bags , 500kg big bags

1x20fcl = 17mts without pallets and 14mts with pallets for 25kg kraft bags

1x20fcl = 10mts for 500kg big bags with pallets

**Storage:**

Keep resin in ventilation place and away from heater, Temperature not exceeding 30'C is recommended in warehouse or during transportation, otherwise resins beads perhaps got lump.

**Notice:**

This product information is indicative and does not include any guarantee.